

FLOOR FINISH



RAVE™

HIGH GLOSS, DURABLE, MULTI-SPEED, SELF-SEALING
FLOOR FINISH FOR HIGH TRAFFIC AREAS
ON RESILIENT AND HARD FLOORS

PRODUCT SPECIFICATION BULLETIN

THE FINEST IN JANITORIAL PRODUCTS, SUPPLIES AND EQUIPMENT SINCE 1946

Product No. 104

PRODUCT DESCRIPTION

Date revised 9/2004

DESCRIPTION: LAWTON'S RAVE is a hard and durable, high solids, high initial gloss, high burnish response gloss, self-sealing floor finish. Its high solids content gives a labor savings bonus by achieving faster film build with fewer coats. Rave has excellent thermoplastic properties that allow superior reparability in response to ultra high speed burnishing or low speed buffing. With these characteristics, RAVE makes an excellent choice for use on resilient or hard floors.

DIRECTIONS

FLOOR PREPARATION: Remove old seals and finishes with LAWTON'S BREEZE or LAWTON'S BLAST OFF – use as directed. Rinse floor well with clean water and allow to thoroughly dry. Seal floor with LAWTON'S CLASSIC SEAL (optional). Apply 1 or 2 coats of seal as directed.

APPLICATION: Apply 2 to 4 thin coats of LAWTON'S RAVE, using a clean finish mop, allowing at least 30 minutes dry time between coats depending on temperature and humidity conditions.

MAINTENANCE: The following is a regular maintenance program. For high maintenance floors see LAWTON INFORMATION BULLETIN on FLOOR CARE SYSTEMS. Sweep & dust mop daily. Reducing soil load extends the life and appearance of your finish.

Important - Use entrance mats to reduce gritty soil.

1. Damp-mop or auto scrub 3 to 5 times per week with LAWTON'S NLC.
2. Buff or burnish weekly or as needed depending on soil load and traffic conditions.
3. Deep scrub monthly or as needed using LAWTON'S NLC or LAWTON'S RESULTZ with a green pad then recoat with 1-2 coats of RAVE.

FUTURE CARE: Complete strip and finish 2 times per year or as needed. Apply 1-2 coats of seal (optional) and 2-4 coats of RAVE.

CAUTIONS

CAUTION: Keep out of reach of children. Any liquids spilled on a finished floor will cause a hazardous slippery condition. Clean up of spills should have immediate attention. Avoid eye contact. For eye contact, rinse with water. If irritation persists, get medical help. Do not swallow. If swallowed get medical help immediately.

WARNING: Do not pour unused finish back into container, as it will damage the product.

CUIDADO: Mantenerlo alejado del alcance de los niños. La limpieza de los derrames requiere atención inmediata. Evite contacto con los ojos. Si tiene contacto con los ojos, enjuague bien con agua. Si la irritación persiste, busque ayuda médica. No lo ingiera. Si lo ingiere busque ayuda médica inmediatamente.

AVISO: No vuelva a vaciar el resto del producto que no utilizó adentro del envase original ya que esto dañará el producto.

HAZARDOUS INGREDIENTS:

Diethyleneglycolmonoethylether	CAS NO. 111-90-0
Tributoxyethylphosphate	CAS NO. 78-51-3
Dipropyleneglycolmonomethylether	CAS NO. 34590-94-8

PROTECTIVE EQUIPMENT

It is recommended to wear protective gloves and protective eyewear when using this or any chemical cleaning product. When spray applying, ventilation and breathing protection is recommended.

TECHNICAL DATA

Nonvolatile solids	25 ± .5% by wt.
Color and appearance	Milk white liquid.
Odor	Mild ammonia odor.
Viscosity	Water thin.
pH	9.0 ± .5 @ 25°C.
Specific Gravity	1.030 @ 25°C.
Weight per gallon	8.56 lbs. per gallon.
Dry time	20 min.
Cure time to recoat	30 min.
Leveling	Excellent.
Gloss	Excellent.
Detergent resistance	Excellent.
Removability	Good.
Slip resistance	Passes standard.
Nonyellowing	Good.
Dry film clarity	Excellent.
Freeze / thaw stability	Passes standard.
Flash point	Nonflammable.
Shelf life (stored properly)	1 year.

READY TO USE

LAWTON BROS., INC. MANUFACTURING CHEMISTS

ORLANDO

2515 DINNEEN AVENUE
P.O. BOX 547635
ORLANDO, FL 32854-7635
PH: 407-291-2501 ● 800-432-0813
FAX: 407-290-0471

CLEARWATER BRANCH

14420 - 60TH STREET NORTH
CLEARWATER, FL 33760
PH: 727-531-1179 ● 800-328-3210
FAX: 727-531-4566

OCALA BRANCH

1507 SOUTH PINE AVENUE
OCALA, FL 34474
PH: 352-629-8810 ● 800-421-5777
FAX: 352-629-3797

MELBOURNE BRANCH

114 SOUTH BABCOCK STREET
MELBOURNE, FL 32901
PH: 321-951-0861
FAX: 321-951-9210