

FLOOR FINISH



VISION™

**EASY CARE • MULTI-SPEED BUFFABLE
HIGH GLOSS • THERMOPLASTIC FLOOR FINISH**

PRODUCT SPECIFICATION BULLETIN

THE FINEST IN JANITORIAL PRODUCTS, SUPPLIES AND EQUIPMENT SINCE 1946

Product No. 105

PRODUCT DESCRIPTION

Date revised 9/2004

DESCRIPTION: *LAWTON'S VISION* is a hard and durable, high initial gloss, high burnish response gloss, self-sealing floor finish. *VISION* has excellent thermoplastic properties that allow superior reparability in response to ultra high speed burnishing or low speed buffing. With these characteristics, *VISION* makes an excellent choice for use on resilient or hard floors.

DIRECTIONS

FLOOR PREPARATION: Remove old seals and finishes with *LAWTON'S BREEZE* or *LAWTON'S BLAST OFF* – use as directed. Rinse floor well with clean water and allow to thoroughly dry. Seal floor with *LAWTON'S CLASSIC SEAL* (optional). Apply 1 or 2 coats of seal as directed.

APPLICATION: Apply 2 to 4 thin coats of *LAWTON'S VISION*, using a clean finish mop, allowing at least 30 minutes dry time between coats depending on temperature and humidity conditions.

MAINTENANCE: The following is a regular maintenance program. For high maintenance floors see *LAWTON INFORMATION BULLETIN* on *FLOOR CARE SYSTEMS*. Sweep & dust mop daily. Reducing soil load extends the life and appearance of your finish.

Important - Use entrance mats to reduce gritty soil.

1. Damp-mop or auto scrub 3 to 5 times per week with *LAWTON'S NLC*.
2. Buff or burnish weekly or as needed depending on soil load and traffic conditions.
3. Deep scrub monthly or as needed using *LAWTON'S NLC* or *LAWTON'S RESULTZ* with a green pad then recoat with 1-2 coats of *VISION*.

FUTURE CARE: Complete strip and finish 2 times per year or as needed. Apply 1-2 coats of seal (optional) and 2-4 coats of *VISION*.

CAUTIONS

CAUTION: Keep out of reach of children. Any liquids spilled on a finished floor will cause a hazardous slippery condition. Clean up of spills should have immediate attention. Avoid eye contact. For eye contact, rinse with water. If irritation persists, get medical help. Do not swallow. If swallowed get medical help immediately.

WARNING: Do not pour unused finish back into container, as it will damage the product.

CUIDADO: Mantenerlo alejado del alcance de los niños. La limpieza de los derrames requiere atención inmediata. Evite contacto con los ojos. Si tiene contacto con los ojos, enjuaguese bien con agua. Si la irritación persiste, busque ayuda médica. No lo ingiera. Si lo ingiere busque ayuda médica inmediatamente.

AVISO: No vuelva a vaciar el resto del producto que no utilizó adentro del envase original ya que esto dañará el producto.

HAZARDOUS INGREDIENTS:

Diethyleneglycolmonoethylether.....	CAS NO. 111-90-0
Tributoxyethylphosphate.....	CAS NO. 78-51-3
Dipropyleneglycolmonomethylether.....	CAS NO. 34590-94-8

PROTECTIVE EQUIPMENT

It is recommended to wear protective gloves and protective eyewear when using this or any chemical cleaning product. When spray applying, ventilation and breathing protection is recommended.

TECHNICAL DATA

Nonvolatile solids.....	20 ± .5 % by wt.
Color and appearance.....	Milk white liquid.
Odor.....	Mild ammonia odor.
Viscosity.....	Water thin.
pH.....	9.0 ± .5 @ 25°C.
Specific Gravity.....	1.020 @ 25°C.
Weight per gallon.....	8.48 lbs. per gallon.
Dry time.....	20 min.
Cure time to recoat.....	30 min.
Leveling.....	Excellent.
Gloss.....	Excellent.
Detergent resistance.....	Excellent.
Removability.....	Good.
Slip resistance.....	Passes standard.
Nonyellowing.....	Good.
Dry film clarity.....	Excellent.
Freeze / thaw stability.....	Passes standard.
Flash point.....	Nonflammable.
Shelf life (stored properly).....	1 year.

READY TO USE

LAWTON BROS., INC. MANUFACTURING CHEMISTS

ORLANDO

2515 DINNEEN AVENUE
P.O. BOX 547635
ORLANDO, FL 32854-7635
PH: 407-291-2501 • 800-432-0813
FAX: 407-290-0471

CLEARWATER BRANCH

14420 - 60TH STREET NORTH
CLEARWATER, FL 33760
PH: 727-531-1179 • 800-328-3210
FAX: 727-531-4566

OCALA BRANCH

1507 SOUTH PINE AVENUE
OCALA, FL 34474
PH: 352-629-8810 • 800-421-5777
FAX: 352-629-3797

MELBOURNE BRANCH

114 SOUTH BABCOCK STREET
MELBOURNE, FL 32901
PH: 321-951-0861
FAX: 321-951-9210